

## MoldMAX HH<sup>®</sup> Alloy

Materion's MoldMAX HH (High Hard) Alloy is the premier copper mold alloy. This alloy has a hardness and strength comparable with standard tool steel but its thermal conductivity is at four to six times higher. MoldMAX HH Alloy is used for injection mold cores and cavities and blow mold pinch-offs. Its high hardness provides durability in applications where other high conductivity copper alloys fail. The alloy resists galling against other mold alloys, including itself.

### Chemical Composition (Weight Percent)

Alloy	Beryllium	Cobalt	Copper
MoldMAX HH Alloy	1.6 - 2.0	0.2 - 0.3	Balance

### Typical Physical Properties

Elastic Modulus	Melting Point (Solidus)	Density	Thermal Expansion (20 - 200 °C)	Thermal Conductivity (100 °C)	Heat Capacity (100 °C)
19,000 ksi 131 GPa	~1600 °F ~870 °C	0.302 lb/in <sup>3</sup> 8.36 g/cm <sup>3</sup>	9.7 x 10 <sup>-6</sup> in/in °F 17.5 x 10 <sup>-6</sup> °C <sup>-1</sup>	75 BTU/hr·ft·°F 130 W/m·°C	0.10 BTU/lb·°F 0.41 J/g·°C

### Typical Mechanical Properties\*

0.2% Offset Yield Strength	Ultimate Tensile Strength	Fatigue Strength 10 <sup>7</sup> Cycles (R=-1)	Elongation	Impact Strength	Hardness
145 ksi 1000 MPa	170 ksi 1170 MPa	> 45 ksi > 310 MPa	5%	4 ft·lb 5 J	40 HRC

\*Properties may vary by shape and thickness.

## Forms Available

Rounds, square and rectangular bars, plate and forged rings.

## Related Information

Additional technical information on MoldMAX® products can be obtained by visiting [www.MoldMax.com](http://www.MoldMax.com) or by calling +1.800.375.4205. For pricing and availability in North America, contact a sales location.

## Health and Safety

Processing beryllium-containing alloys poses a health risk if safe practices are not followed. Inhalation of airborne beryllium can cause serious lung diseases in some individuals. Occupational safety and health regulatory agencies worldwide have set mandatory limits on occupational respiratory exposures. Read and follow the guidance in the Safety Data Sheet (SDS) before working with this material. The SDS and additional important beryllium health and safety information and guidance can be found at [berylliumsafety.com](http://berylliumsafety.com), [berylliumsafety.eu](http://berylliumsafety.eu) and [Materion.com](http://Materion.com). For questions on safe practices for beryllium-containing alloys, contact the Materion Product Stewardship Group at +1.800.862.4118 or contact us by email at [Materion-PS@Materion.com](mailto:Materion-PS@Materion.com).

### Disclaimer:

Only the buyer can determine the appropriateness of any processing practice, end-product or application. Materion does not make any warranty regarding its recommendations, the suitability of Materion's product, or its processing suggestions for buyer's end product, application or equipment.

The properties presented on this data sheet are for reference purposes only, intended only to initiate the material selection process. They do not constitute, nor are they intended to constitute, a material specification. Material will be produced to one of the applicable industry standards, if any, listed in the Industry Standards and Specification section.

Actual properties may vary by thickness and/or part number. Please contact your local sales engineer for detailed properties to be used in simulation.

Any properties marked as preliminary are subject to change at any time as the manufacturing process is further refined.

### MATERION Alloys and Composites

6070 Parkland Boulevard  
Mayfield Heights, OH 44124 USA

### Contact Us:

[materion.com/ContactPAC](http://materion.com/ContactPAC)  
+1.800.375.4205

### MATERION Global Headquarters

6070 Parkland Boulevard  
Mayfield Heights, OH 44124 USA

DS-AM-278 © 2021 Materion Corporation