



BrushForm® 158 Strip - TM10 Temper

Materion's BrushForm 158 Strip is a high-performance, heat treated spinodal copper-nickel-tin alloy designed to provide optimal formability and strength characteristics. TM10 provides excellent flatness and stiffness coupled with high resistance to vibration, fatigue and impact loading. This makes it ideal for voice coil motor springs in optical image stabilization systems.



Chemical Composition (Weight Percent)

Alloy	Nickel	Tin	Copper
BrushForm 158 Strip	14.5 - 15.5	7.5 - 8.5	Balance

Physical Properties

Elastic Modulus (GPa)	Density	Typical Electrical Conductivity	Thermal Expansion Coefficient	Relative Magnetic Permeability	Poisson's Ratio
120	9.0 g/cm ³	7% IACS 4 MS/m	16.4 x 10 ⁻⁶ m/m °C	< 1.001	0.3

Mechanical Properties

Temper	0.2% Offset Yield Strength (MPa)	Ultimate Tensile Strength (MPa)	Elongation*	Hardness (HV)
TM10	1135 - 1345	1205 - 1450	1.0% min.	370 min.

^{*}Percent elongation valid only for strip greater than 0.10 mm thick.

Standard Availability

Mill hardened tempered strip: 0.025 - 0.12 mm gauge.

Industry Standards and Specifications

UNS C72900, ASTM B743

Related Information

Additional technical information on BrushForm 158 strip may be obtained by phoning +1.800.375.4205. For pricing and availability, phone +1.800.521.8800.

Disclaimer

Only the buyer can determine the appropriateness of any processing practice, end-product or application. Materion does not make any warranty regarding its recommendations, the suitability of Materion's product, or its processing suggestions for buyer's end product, application or equipment.

The properties presented on this data sheet are for reference purposes only, intended only to initiate the material selection process. They do not constitute, nor are they intended to constitute, a material specification. Material will be produced to one of the applicable industry standards, if any, listed in the Industry Standards and Specification section.

Actual properties may vary by thickness and/or part number. Please contact your local sales engineer for detailed properties to be used in simulation.

Any properties marked as preliminary are subject to change at any time as the manufacturing process is further refined.